

ARCHCO 453 EPOXY

Two-Part Epoxy for Industrial Storage and Process Tanks and Pipelines

Description

Archco 453 is a 70% solids, two-part, epoxy phenolic-novolac system designed to produce a lining with excellent chemical and temperature resistance over a wide range of temperatures and pressures.

Uses

Corrosion protection for industrial storage and process chemical tanks and pipelines, high pressure crude oil pipes and separation tanks. Also used as a protective coating for highly corrosive environments. Provides exceptional resistance over a wide range of temperatures and pressures.

Features

- 20-30 mils (0.50 - 0.76 mm) thickness DFT, if applied in a two coat system
10 to 12 mils (0.25 - 0.30 mm) per coat.
- Does not require baking to cure
- Excellent chemical resistance under ambient cure conditions
- Exceptional resistance to a wide variety of chemicals and solvents
- High gloss provides easy cleaning

Application

All contaminants shall be removed from the steel surface to be coated. Oil and grease should be removed in accordance to SSPC-SP-1. Surfaces shall be free from projections; sharp edges, high points and fillets must be ground smooth including all corners. Prepare surfaces by grit blasting to a clean, near-white finish, SSPC-SP 10, NACE No. 2 or Sa 2-1/2. Appropriate angular grit shall be used to achieve a 3 to 5 mil (0.08 - 0.13 mm) anchor profile. Vacuum tank floor to remove grit prior to coating.

To spray the Archco 453 Epoxy, a plural-component airless spray unit with a proportioning pump capable of a volume mixing ratio of 4:1 or single-leg airless unit can be used. Standard ancillary equipment should include minimum 10 gallon (38 L) hoppers, 2 each static mixers, 25 ft. max x 1/4" (7.6m x 6.4 mm) whip hose, and mastic gun with a 23 to 27 thou (0.58 - 0.68 mm) tip. Part A should be heated to 100-120°F (38 - 49°C) and Part B should be heated to 90-110°F (32 - 43°C). Hose bundle shall be set at 100-120°F (38 - 49°C). On the single-leg airless unit, it shall be a minimum of 68:1 airless pump. A wet-on-wet spray technique should be used to achieve a minimum thickness of 20 mils (0.508 mm) DFT. The coating thickness should be measured using a wet-film thickness gauge. The equipment settings are only guidelines and may vary based on equipment and specific application. Thinning not required or desirable but at lower temperatures a small amount of Archco 400 E Thinner (5% or less) can be added.

For complete application instructions, please refer to Archco 453 Epoxy application specifications.



Archco 453 Epoxy

TECHNICAL DATA

PROPERTIES	VALUE
Solids Content	
By Weight	85%
By Volume	70%
Base Component — unmixed @ 77°F (25°C)	
Specific Gravity	1.7
Viscosity	15,000 cP
Color	Blue
Hardener — unmixed @ 77°F (25°C)	
Specific Gravity	1.0
Viscosity	100 cP
Color	Amber
Mixed Material — mixed @ 77°F (25°C)	
Specific Gravity	1.6
Viscosity	10,000 cP
Color	Blue
Mixing Ratio (A/B) by Volume	4 Parts Base: 1 Part Hardener
by Weight	7 Parts Base: 1 Part Hardener
Cure Times	
Pot Life @ 77°F (25°C)	3 hours
Pot Life @ 97°F (36°C)	1 hour
Time to Dry @ 50°F (10°C)	20 hours
Time to Dry @ 77°F (25°C)	7 hours
Recoat Window	
@ 77°F (25°C)	30 days
Theoretical Coverage	80 ft ² /20 mls/gallon (2.0 m ² /0.48 mm/Liters)
Thickness per coat	20-30 mils (0.50 - 0.76 mm) DFT, if applied in a two coat system 10 to 12 mils (0.25 - 0.30 mm) per coat.
Holiday Detection – based on min. mil.	100 volts/mil (3936 volts/mm)
Hardness (ASTM D2240-02)	Shore D 82 +/-2
Adhesion to Steel	3,200 psi (22.1 MPa)
Application Temperature	50-130°F (10-54°C)
Service Temperature	35-300°F (2-149°C)

STORAGE: Minimum 24 months when stored in original containers @ 40°F (4°C) to 105°F (41°C). On job site where temperatures are below 50°F (10°C) product should be kept warm to allow for easy transfer into storage hoppers for warming to proper spraying temperatures.

CLEANING: Clean equipment with MEK or equivalent solvent cleaner, such as Archco 400E Thinner.

HEALTH AND SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See material safety data sheet for further information.

PACKAGING: 25 gallon (95 Liters) and 5 gallon (19 Liters) kits. Other sizes available upon request.



HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 1-281-821-3355
Fax: 1-281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 1-416-291-3435
Fax: 1-416-291-0898

e-mail: info@premiercoatings.com

www.premiercoatings.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.