

PROTAL™ 650 CTR

Environmentally Friendly Alternative to Coal Tar Epoxy

Description

Protal 650 CTR (Coal Tar Replacement) is a two-part product formulated to replace coal tar epoxy. It is based on polyamide chemistry designed as an environmentally friendly alternative to hazardous coal tar epoxies.

Uses

For long-term corrosion protection of steel and concrete substrates against water and seawater corrosion. Designed to coat steel piles, sheet piles, lock gates, reservoirs or wherever coal tar epoxy would normally be used.

Features

- Excellent resistance to water/seawater
- Good impact resistance
- Excellent flexibility, hardness, and adhesion
- High build 16 to 26 mils (406 to 660 microns) in one coat
- Touch dry 3 hours at 77°F (25°C)
- Can be brush or spray applied
- Environmentally friendly
- Non-Carcinogenic replacement for coal tar epoxy

Application

Steel: All contaminants shall be removed from the steel surface to be coated. Remove oil, dust, and grease and other contaminants that could interfere with adhesion of the coating. Surfaces shall be free from projections, sharp edges, high points and fillets must be ground smooth including all corners. For immersion service, prepare surfaces by grit blasting to a clean near white finish, SSPC-SP 10 or NACE No. 2. Appropriate angular grit shall be used to achieve a 2.0 to 4.0 mil (50 to 100 microns) anchor profile. For non-immersion service, prepare surfaces using SSPC - SP2 / SP3.

Concrete: Concrete must be cured 28 days at 77°F (25°C) and 50% relative humidity. All surfaces shall be prepared in accordance with ASTM D4258 and ASTM D4259. All voids in concrete shall be filled and repaired.

Spray: A single leg airless unit shall be used. The unit shall be a minimum of 68:1 airless pump. A wet-on-wet spray technique should be used to achieve 16 to 26 mils (406 to 660 microns). The coating thickness should be measured using a wet-film thickness gauge. **Brush:** Use a medium bristle brush. **Roller:** Use a short-nap roller cover with phenolic core. **Mixing:** Power mix both A & B separately then combine and power mix thoroughly for two minutes. Do not mix partial kits.

For complete application instructions please refer to Protal 650 CTR Application Specifications.

Protal™ 650 CTR

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Solids by Volume	76%	76%
Specific Gravity	1.4	1.4
Minimum Dewpoint/Substrate Differential	Dewpoint +5°F	Dewpoint +3°C
Minimum Substrate Temperature	50°F	10°C
Theoretical Coverage	76 SF/Gal @ 16 mils	20 SF/L @ 406 microns
Hardness (ASTM D-2240-02)	Shore D 75	Shore D 75
Spray Equipment Required	68:1 airless	68:1 airless
Hot Salt Fog 95°F (35°C) ASTM B117 (1500 Hrs)	Excellent	Excellent
Wet Film Thickness Per Coat*		
(minimum)	16 mils	406 microns
(maximum)	26 mils	660 microns
Dry Film Thickness Per Coat*		
(minimum)	12 mils	304 microns
(maximum)	19 mils	482 microns
Pot Life @ 77°F (25°C)	2 hours	2 hours
@ 90°F (32°C)	1 hour	1 hour
Dry to Touch @ 50°F (10°C)	6 hours	6 hours
@ 77°F (25°C)	3 hours	3 hours
@ 90°F (32°C)	1.5 hours	1.5 hours
Final Cure Immersion service @ 50°F (10°C)	14 days	14 days
@ 77°F (25°C)	7 days	7 days
@ 90°F (32°C)	5 days	5 days
Adhesion - ASTM D4541	3,300 psi	22.7 MPa
Abrasion Resistance, 1000 cycles, CS-17 wheels, 1 kg load – ASTM D4060	152 mg loss	152 mg loss
Thinner	Not recommended	
Ratio by volume (A to B)	4:1	
Gloss	Semi-Gloss	
Color	Black - Other Colors Available	

STORAGE: Minimum 18 months when stored in original unopened containers at 41°F (5°C) to 110°F (43°C).

CLEANING: Clean equipment with MEK, Archco™ 400E Thinner or equivalent solvent cleaner.

HEALTH AND SAFETY: Wear protective clothing and ensure adequate ventilation. Avoid contact with skin and eyes. See safety data sheet for further information.

PACKAGING: 1 gallon (3.8 liter) and 5 gallon (19 liter) kits



HOUSTON:
9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 1-281-821-3355
Fax: 1-281-821-0304

TORONTO:
90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 1-416-291-3435
Fax: 1-416-291-0898

e-mail: info@premiercoatings.com

www.premiercoatings.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.